





sentriclad


architectural metals




Regal White*
IR = .68
IE = .89




Bone White*
IR = .65
IE = .90



Stone White*
IR = .62
IE = .90



Almond*
IR = .57
IE = .90



Sandstone*
IR = .51
IE = .89



Surrey Beige*
IR = .41
IE = .90



Sierra Tan*
IR = .38
IE = .90



Slate Gray
IR = .22
IE = .91



Musket Gray
IR = .15
IE = .90



Medium Bronze
IR = .10
IE = .90



Mansard Brown
IR = .08
IE = .93



Dark Bronze
IR = .07
IE = .90



Old Town Gray*
IR = .25
IE = .90



Hemlock Green
IR = .21
IE = .90



Patina Green*
IR = .26
IE = .89



Teal
IR = .13
IE = .88



Classic Green
IR = .14
IE = .90



Hartford Green
IR = .09
IE = .90



Charcoal Gray
IR = .10
IE = .90



Matte Black
IR = .07
IE = .89



Slate Blue
IR = .22
IE = .89



Regal Blue
IR = .16
IE = .88



Apothecary Blue^P
IR = .26
IE = .88



Burgundy*
IR = .25
IE = .90



Colonial Red
IR = .23
IE = .92



Terra Cotta*
IR = .38
IE = .89



Banner Red^{*P}
IR = .48
IE = .89



Pewter^P
IR = .23
IE = .87



Bright Silver^{*P}
IR = .57
IE = .77



Bright Copper^{*P}
IR = .45
IE = .86



* = Energy Star Approved for steep slope applications
IR = Initial Reflectivity
IE = Initial Emissivity
P = Subject to premium pricing

Colors shown are as close to actual colors as allowed by the printing process. Actual metal samples are available.
Due to product improvements, changes and other factors, we reserve the right to change or delete information herein without prior notice.

Flat Sheet Color Availability

	Steel				Aluminum				
	26ga LG	24ga	24ga LG	22ga	18ga	.032"	.040"	.050"	.063"
PVDF									
Regal White		•	•	•	•	•			•
Bone White		•		•		•	•	•	
Stone White		•				•	•	•	
Almond		•	•			•	•	•	
Sandstone		•	•	•		•	•	•	
Surrey Beige		•		•		•	•	•	
Sierra Tan		•	•			•	•	•	
Slate Gray	•	•	•	•		•	•		
Musket Gray		•				•			
Medium Bronze		•	•				•	•	
Mansard Brown		•				•	•	•	
Dark Bronze	•	•		•	•	•	•	•	•
Old Town Gray		•	•						
Hemlock Green		•							
Patina Green		•	•			•			
Teal		•	•						
Classic Green	•	•	•			•	•		
Hartford Green	•	•				•			
Charcoal Gray	•	•				•			
Matte Black	•	•				•	•		
Slate Blue	•								
Regal Blue		•	•			•			
Apothecary Blue +		•						•	
Burgundy		•							
Colonial Red	•	•				•			
Terra Cotta		•	•						
Banner Red +		•				•			
PVDF MICA									
Pewter +		•							
Bright Silver +		•					•		
Bright Copper +		•							
POLYESTER									
White/White						•			
Dark Bronze/White						•			
Matte Black/White						•	•		
000250" ANODIZED									
Clear						•	•	•	
Dark Bronze							•		

Notes on availability:

1. 24ga, .032", .040", .050" & .063" are standard 48.25" width, 22ga & 18ga are 44.375" for painted items.
2. Standard inventory is non-embossed. Please contact us for the availability of stucco embossing.
3. Protective strippable film is available upon request.
4. Apothecary Blue, Banner Red, Pewter, Bright Copper and Bright Silver are subject to premium pricing.
5. Subject to change without notice.

Paint Performance Properties	Hot Dipped Galvanized Steel or Galvalume	Aluminum
Accelerated Weathering ASTM D 4587 (Drew Cycle Weatherometer)	Hours: 3,000 Total Chalk: Rating 8 Color: 5ΔE Hunter units max	Hours: 3,000 Total Chalk: Rating 8 Color: 5ΔE Hunter units max
ASTM G 23	Hours: 5,000 Total Chalk: Rating 8 Color: 5ΔE Hunter units max	Hours: 5,000 Total Chalk: Rating 8 Color: 5ΔE Hunter units max
Salt Spray ASTM B 117	Hours: 1,000 Total Scribe: Rating 7 1/16" (1.6mm) Field: Rating 10, no blisters	Hours: 3,000 Total Scribe: Rating 10, no creepage Field: Rating 10, no blisters
Humidity ASTM D 2247	Hours: 2,000 Total Rating: 10, no blisters	Hours: 3,000 Total Rating: 10, no blisters
Formability ASTM D 4145	2T	2T
ASTM D 522 (Elongation over 1/8" mandrel)	No cracking No loss of adhesion	No cracking No loss of adhesion
Pencil Hardness ASTM D 3363	HB-2H	HB-2H
Abrasion Resistance ASTM D 968	50-80 Liters of falling sand	50-80 Liters of falling sand
Specular Gloss ASTM D 523	20-35 at 60°	20-35 at 60°
Reverse Impact ASTM D 2794	3 x Metal thickness in inch-lbs. No loss of adhesion	1 1/2 x Metal thickness in inch-lbs. No loss of adhesion
Flame Test ASTM E 84	Class A rated coating	Class A rating coating

www.sentrigard.com

Sentriclad's standard architectural colors and finishes feature 70% polyvinylidene fluoride (PVDF) resin paint systems to ensure long term color retention and performance. Custom colors and finishes are also available. Minimum quantities and set up charges may apply. Consult www.sentrigard.com for additional information.



Capitol Heights, MD
1-800-234-6242

Lynchburg, VA
1-800-925-6242

Norfolk, VA
1-800-283-6242

Richmond, VA
1-800-288-6242

Roanoke, VA
1-800-289-6242

Charlotte, NC
1-800-365-6242

Greensboro, NC
1-800-678-6242

Raleigh, NC
1-800-456-6242

Columbia, SC
1-800-849-8557

Greenville, SC
1-800-727-6242

Atlanta, GA
1-800-716-6242

Nashville, TN
1-866-794-5606

Orlando, FL
1-866-787-6268

Boca Raton, FL
1-866-489-6242



Baltimore, MD
1-800-875-7826

Lorton, VA
1-571-339-1100

Herndon, VA
1-866-765-8556